



MATERIAL TEST DATA SHEET MD29 – 18/07/2007 Page 1 of 2

COMPOUND: F157 (LK)

POLYMER TYPE: TETRAFLUORETHYLENE/PROPYLENE CO-POLYMER (AFLAS®) 75 (+/-5°)

Physical Properties

| Test | Units | Typical Values |
|----------|------------------------------------|---|
| Method | 00 | |
| | | Black |
| ISO 48 | °IRHD | 76 |
| ISO 37 | MPa | 22.2 |
| ISO 37 | MPa | 8.10 |
| ISO 37 | % | 199 |
| ISO 34 | N/mm | 30.0 |
| ISO 2781 | g/cm3 | 1.59 |
| | ISO 48 ISO 37 ISO 37 ISO 37 ISO 37 | ISO 48 °IRHD ISO 37 MPa ISO 37 MPa ISO 37 % ISO 34 N/mm |


Description

This compound has excellent physical properties and offers good resistance to acids, bases, water, amines and high temperature steam. It is particularly useful in gas and oil stripping, where mixtures of Hydrocarbons, Amines and H2S are encountered. Service Temperature -5°C (23°F) to 200°C (390°F).

Aflas® is a registered trademark of Ashi Glass Corporation

Compression Set

Typical Compression Set Values in Air @ 200°C Under 25% Strain (ISO 815)



These properties should not be regarded as specifications, but only as typical properties of the material described. It is intended for use by persons having technical skills and understanding of the seal and gasket design. Since the conditions of use are outside our control, nor have we designed the product shape, we can make no warranties, express or implied and assume no liability in connection with any use of this information.

Since development and improvement of compounds is a continuing process, Gapi reserves the right to modify their composition and characteristics. Uncontrolled Copy.





MATERIAL TEST DATA SHEET MD29 - 18/07/2007 Page 2 of 2

COMPOUND: F157 (LH)

POLYMER TYPE: TETRAFLUORETHYLENE/PROPYLENE CO-POLYMER (AFLAS®) 75 (+/-5°)

AIR-AGEING

| Property | Test Standard | Units | Typical Values | |
|---------------------------|---------------|--------|----------------|--|
| (After 168 Hours @ 175°C) | | | | |
| HARDNESS CHANGE | ISO 188 | °IRHD | -2 | |
| TENSILE CHANGE | ISO 188 | % | +6.2 | |
| ELONGATION CHANGE | ISO 188 | % | +6.5 | |
| | | | | |
| Property | Test Standard | Units | Typical Values | |
| (After 336 Hours @ 175°C) | | | | |
| HARDNESS CHANGE | ISO 188 | °IRHD | -3 | |
| TENSILE CHANGE | ISO 188 | % | +6.7 | |
| ELONGATION CHANGE | ISO 188 | % | +0.5 | |
| | | | | |
| Absorption Test | | | | |
| Droporty | Tost Standard | Linita | Typical Values | |

| Though peron Tout | | | | |
|---------------------------|---------------|-------|----------------|--|
| Property | Test Standard | Units | Typical Values | |
| (After 168 Hours @ 175°C) | | | | |
| IRM 901 Oil | | | | |
| Volume Change | ISO 1817 | % | +3.57 | |
| | | | | |
| IRM 903 Oil | | | | |
| Volume Change | ISO 1817 | % | +5.72 | |
| | | | | |
| Distilled Water | | | , | |
| | 100 1017 | 2/ | 2.24 | |
| Volume Change | ISO 1817 | % | +3.34 | |