



PRODUCT DATA SHEET MD134 – 14/07/2021 Page 1 of 1

## Compound GPlast<sup>™</sup> LT-45 Ultra Low Temperature (UN) POLYMER TYPE: Perfluoroelastomer FFKM75 (+/-5°)

## **Physical Properties**

Property	Test	Units	Typical Values	
	Method			
COLOUR			Black	
HARDNESS	ISO 48	°IRHD	75	
TENSILE STRENGTH	ISO 37	MPa	9.67	
MODULUS @ 100%	ISO 37	MPa	3.11	
ELONGATION @ BREAK	ISO 37	%	280	
TEAR STRENGTH	ISO 34	N/mm	12.4	
SPECIFIC GRAVITY	ISO 2781	g/cm3	1.99	
COMPRESSION SET VALUE IN AIR				
25% STRAIN – 24HRS @ 204°C	ISO 815	%	19.9	
LOW TEMPERATURE TR10	ISO 2921	°C	-30	

## **Description**

This Black low temperature material provides an excellent temperature range from -45°C (-49°F) up to +240°C (+464°F) and has similar chemical resistance to that of PTFE but with elastomeric properties comparable to standard fluorocarbon rubbers.

Along with all our GPlast<sup>™</sup> range, this grade is suitable for use in a wide range of applications where other polymers are not suitable. Do not use any GPlast<sup>™</sup> grade with molten alkali metals.

## **Chemical Resistance**

1. Suitable, little or no effect. 2. Minor to moderate effect, not maximum resistance. 3. Moderate to severe effect – may be useful in some limited applications. 4. Unsuitable and not recommended – severe effect.

Chemical Group	Rating
Aromatics / Aliphatic Oils	1
Acids	2
Alkalis	1
Alcohols	1
Aldehydes	1
Amines	1 1
Amines >70°C	2
Ethers	1
Ethylene Oxide	1
Esters	1
Ketones	1
Propylene Oxide	1
Steam/Hot Water	1
Strong Oxidisers	1

More detailed information available on request.

Since development and improvement of compounds is a continuing process, Gapi reserves the right to modify their composition and characteristics. Uncontrolled Copy