

Compound GPlast™ T141 Low Hardness Green (UB)
POLYMER TYPE: Perfluoroelastomer FFKM65 (60°-65°)

Physical Properties

Property	Test Method	Units	Typical Values
COLOUR			Green
HARDNESS	ISO 48	°IRHD	65
TENSILE STRENGTH	ISO 37	MPa	14.2
MODULUS @ 100%	ISO 37	MPa	6.2
ELONGATION @ BREAK	ISO 37	%	177
TEAR STRENGTH	ISO 34	N/mm	14.7
SPECIFIC GRAVITY	ISO 2781	g/cm ³	2.20
COMPRESSION SET VALUE IN AIR 25% STRAIN – 24HRS @ 204°C	ISO 815	%	30.7

Description

This Green material provides excellent temperature resistance up to +260°C (+500°F) and has similar chemical resistance to that of PTFE but with elastomeric properties comparable to standard fluorocarbon rubbers. Along with all our GPlast™ range, this grade is suitable for use in a wide range of applications where other polymers are not suitable. Do not use any GPlast™ grade with molten alkali metals. Service Temperatures +260°C (+500°F) to -15°C (+5°F).

Chemical Resistance

1. Suitable, little or no effect. 2. Minor to moderate effect, not maximum resistance. 3. Moderate to severe effect – may be useful in some limited applications. 4. Unsuitable and not recommended – severe effect.

Chemical Group	Rating
Aromatics / Aliphatic Oils	1
Acids	1
Alkalies	1
Alcohols	1
Aldehydes	1
Amines	1
Ethers	1
Ethylene	1
Esters	1
Ketones	1
Propylene Oxide	1
Steam/Hot Water	1
Strong Oxidisers	1

More detailed information available on request.